

09764-8

- 13



3

- 5/25/90

~~The process according to claim 6 wherein the mixture reflux is conducted for 16 hours.~~

In re Alejandro Chio ARJONA et al.
U.S. Application Serial No. 09/750,483

10. The process according to claim 6 wherein the catalyst is triethylamine.
11. The process according to claim 10 wherein the triethylamine is added at a rate of 0.178 l/hr per Kg of product during a 3-5 hour period.
12. The process according to claim 6 wherein the aromatic isocyanate is methylene diisocyanate.
13. The process according to claim 6 wherein the diglycinate is crystallized at 50°C.
14. The process according to claim 6 wherein the stirring with methylene diisocyanate is at a temperature of 60°C.
15. The process according to claim 6 wherein the catalyst is added at a temperature of up to 180°C.
16. The process according to claim 6 wherein the distilling is conducted at a temperature of 200°C.
17. The process according to claim 6 wherein the cooling is conducted at 70°C.
18. The process according to claim 6 wherein the product has a viscosity of 44 to 47 seconds at 25°C.
19. The process according to claim 6 wherein the catalyst in step (h) is selected from the group consisting of triethylenediamino and 1,4 diazobicyclo (2,2,2) octane.
20. The process according to claim 6 wherein the polyglycolyl urea hydantoin obtained

In re Alejandro Chio ARJONA et al.
U.S. Application Serial No. 09/750,483

has viscosity (Cp) of 4,800 at 15% solids.

21. The process according to claim 6, wherein the the C₁-C₄ aliphatic solvent is methanol.
22. The process according to claim 6, wherein the reflux temperature of the C₁-C₄ aliphatic solvent is 58 - 63°C.

3
PG 23
23. The process according to claim 6, wherein the methyl methyl diglycinate obtained is dried with hot air at 40°C and corresponds to a stereoisomer mixture with a melting point of 95-116°C, of the following formula II:



24. The process according to claim 6, wherein the residues of the mother waters are by-products of the reaction of triethylamine bromohydrate salts which are neutralized with sodium hydroxide and separated through secondary distillation obtaining sodium bromide in solution and 90% triethylamine.
25. Abrasion resistant and flexible coating for insulating electric conductor made from polyglycolyl urea hydantoin according to claim 6.

REMARKS

Claims 1-5 have been cancelled. No new matter has been incorporated by these amendments. Upon entry of the amendments, Claims 6-25 remain in the present application.

In view of the above remarks, it is respectfully submitted that the claims are in condition for examination. In the event that there are any problems which can be expedited by telephone